

ALPHA[®] Vaculoy SACX 0307,0300

LEAD FREE WAVE SOLDER ALLOY

DESCRIPTION

ALPHA Vaculoy SACX0307 is a lead-free alloy suitable for use as a replacement for Sn63 alloy in the wave solder process. The SACX0300 variant is used to stabilize / reduce the copper content in the wave solder bath, this requirement will depend on process conditions. As with all Alpha Metals bar solder, Alpha's proprietary Vaculoy™ alloying process is used to remove certain impurities, particularly oxides. The product is further enhanced with the addition of 2 minor elements to reduce dross formation and improve the joint cosmetics.

FEATURES & BENEFITS

Features:

- ❑ YIELD – Comparable to SAC305, superior performance for bridging compared to Sn99.3/Cu0.7 based alloys.
- ❑ WETTING SPEED – 0.75 seconds typical wetting speed compares to SAC305 at 0.65 sec and superior to Sn99.3/Cu0.7 based alloys at 1.0 sec.
- ❑ DROSS GENERATION – lowest in class due to the Vaculoy process in conjunction with the addition of a dross reducing agent.

Benefits:

- ❑ Lowers Total Cost of Ownership due to the lower material cost, high yields and low dross generation.
- ❑ Gives very good solderability due to the fast wetting speed.
- ❑ Gives very good drainage and hence lower levels of bridges due to the formulation containing Silver.
- ❑ Delivers good performance across a range of flux technologies.

The proprietary Vaculoy process is a highly effective method for removing included oxides from solder. This is extremely important because included oxides generate excessive drossing and increase the viscosity of the solder. Solder with higher viscosity can result in increased soldering defects (i.e solder bridging)

APPLICATION

ALPHA VACULOY SACX0307 is suitable for wave soldering and surface mount applications for electronic assemblers interested in implementing a lead-free process. It is suited to single side and mixed technology boards. A solder pot temperature of 255 - 265° C (491 – 509F) is recommended with a contact time 2.3 – 3.5 seconds. For suitable wave solder fluxes, please see our selector guide. Lead free Reclaim services including dedicated lead free containers are also available, please consult your local sales office.

AVAILABILITY

ALPHA VACULOY SACX0307/0300 is available in 1kg (2.2lb) Bar , chunks , Feeder Ingots and Autofeed Wire

* US Patent 4929423

HEALTH & SAFETY

Please refer to MSDS for advice on proper handling and safety instructions.



Cookson Electronics ASSEMBLY MATERIALS

Issue 5



TECHNICAL SPECIFICATION

Complies with all requirements of RoHS Directive (Article 4.1 of the European Directive 2002/95/EC). Alloy specification for Maximum Lead (Pb) Content = **0.1%**

US Patent 4929423

Material Property	Units	Vaculoy SACX0307
Solidus	Celsius	217
Liquidus	Celsius	228
Hardness	HV	14.1
Density	g/cc	7.33
Specific Heat Capacity	J/kg C	0.17
Stress at MAX Load (N/mm²)	Mean	29.5
	Std Dev	0.64
Elongation at failure (%)	Mean	21.8
	Std Dev	8.8
Thermal Expansion Coefficient	(30 - 100C)/C x 10⁻⁵	1.79
	(100 - 150C)/C x 10⁻⁵	2.30
Silver Content	%	0.3 +0.15/-0.05
Copper Content	%	0.70 +/-0.1
Lead Content	%	Max 0.1%

RECOMMENDED PROCESS SETTINGS

Wave Configuration	Process Parameter	Suggested Process Settings
Single Wave	Pot temperature	255 - 265 Celsius (491 - 509 F)
	Conveyor speed	1.0 - 1.5 m/min (3.3 - 5 ft/min)
	Contact time	2.3 - 2.8 seconds
	Wave Height	1/2 to 2/3 of board thickness
	Dross removal	Once per 8 hour run time
	Copper Check	Every 8,000 boards until 40,000
Dual Wave	Pot temperature	255 - 265 Celsius (491 - 509 F)
	Conveyor speed	1.0 - 1.5 m/min (3.3 - 5 ft/min)
	Contact time	3.0 - 3.5 seconds
	Wave Height	1/2 to 2/3 of board thickness
	Dross removal	Once per 8 hour run time
	Copper Check	Every 8,000 boards until 40,000

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated.



MANAGEMENT OF COPPER LEVELS IN THE SOLDER BATH

Copper should be controlled in the solder bath between 0.7% and 1.0%

Management of the copper level in the wave solder bath is critical to ensure low defects in the soldering process. There is a tendency for the copper levels of the SACX0307 materials to increase due to the leaching effect of the solder wave on the board and components. This effect is at its most severe when using an OSP Copper finish on the PCB.

Studies have shown a typical leaching rate of 0.01% Cu per 1000 boards. Each process is unique this is an indication only of the leaching rate (based on actual data).

It is recommended that the copper is controlled at between 0.7% and max 1.0% for SACX0307 alloy. If the copper levels are higher than 1.0% then this will increase the liquidous temperature which in turn may mean that the solder bath temperature has to be increased to maintain the process yields.

The copper levels in the bath can be controlled by means of adding SACX0300 to the wave solder pot. It may be the case that equilibrium can be attained by continuing with SACX0300 additions as the only means of solder top up, however each process is unique and we would recommend regular analysis of the solder bath so that good control of copper can be maintained.

This analysis service is available from Cookson Electronics Assembly Materials, contact your local office for details.

RECOMMENDED ACTION LEVELS FOR WAVE SOLDER IMPURITIES

Please find below a list of recommended action levels for wave solder bath impurities. For information of specific action plans to bring your solder bath back to an acceptable condition please contact your local sales office.

Table with 3 columns: Element, ACTION Levels, and Notes. Rows include Sn, Pb, As, Cu, Bi, Zn, Fe, Ag, Sb, Ni, Cd, Al, and Au with their respective action levels and notes.

Headquarters
Cookson Electronics Assembly Materials
600 Route 440
Jersey City
NJ 07304, U.S.A.
Tel: +1 (201) 434 6778
Fax: +1 (201) 434 7508
www.alphametals.com

Regional Sales Offices:

Belgium Tel: +32 (0) 14 44 50 00
Brazil Tel: +55 11 4353 2500
France: Tel: +33 (0) 2 41 49 00 11
Germany: Tel: +49 (0)2173 8490 300
Hong Kong: Tel: +852 3190 3100
Hungary Tel: +36 (0) 24 460 72 0
India: Tel: +91 44 625 2666
Ireland: Tel: +353 (0) 1 842 1172
Italy: Tel: +39 (0)2 38 33 11
Japan: Tel: +81 463 53 3333
Korea: Tel: +82 31 499 1451
Mexico: Tel: +52 3 818 9500
Netherlands: Tel: +31 (0) 35 695 5411
Singapore: Tel: +65 6861 1977
Taiwan: Tel: +886 (3) 322 2721
UK: Tel: +44 (0) 1483 793100
USA - Elgin: Tel: +1 (847) 697 1735

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated.