

# ALPHA<sup>®</sup> OM-338 Paste Flux

## No-Clean Rework and BGA Flux

### DESCRIPTION

This No-Clean flux is engineered to be used in the placement and reflow of lead-free solders for BGA attach processes. Before reflow, the flux provides sufficient tack to hold the BGA in place. After reflow the residue is clear, colorless. This paste flux can also be used in the rework of components.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

### APPLICATION GUIDELINES

The flux may be applied by screen printing or pin transfer (substrate) or doctor blade / dip coating (package). It can also be dispensed.

#### Cleaning

Although designed as a no-clean flux system, the reflowed residue may be cleaned with BIOACT<sup>®</sup> SC-10E, BIOACT<sup>®</sup> SC-30, ALPHA SM-110, ALPHA SM-110E, ALPHA BC-2200, Kyzen Micronox<sup>®</sup> MX2501, and Zestron<sup>®</sup> ATRON<sup>®</sup> AC205. Production stencils or pin transfer equipment can be cleaned with BIOACT<sup>®</sup> SC-10.

**TECHNICAL DATA**

Item	Typical Values
Appearance	Smooth, white to off-white paste
Viscosity (Spiral/Malcom)	Typically, 170 to 300 Poise @ 25 °C (5 RPM)
<u>Tack strength (per IPC J-STD-004)</u>	
Initial	6.5 grams / sq mm
6 hr @ 50% RH	6.2 grams / sq mm
24 hr @ 50% RH	6.2 grams / sq mm
Fineness of Grind	<10 µm
Acid Number (mg KOH/g)	140 to 170
Corrosivity	Passes IPC Cu mirror, Cu corrosion
Halide Content	Halide free (ROL0 per IPC J-STD-004)
Moisture Content	< 1.0 % (w/w)
J-STD-004 SIR (pass > 10 <sup>8</sup> )	4.2 x 10 <sup>9</sup> Ohms, 1 Day, un-cleaned
J-STD-004 SIR (pass > 10 <sup>8</sup> )	6.8 x 10 <sup>9</sup> Ohms, 4 Days, un-cleaned
J-STD-004 SIR (pass > 10 <sup>8</sup> )	8.9 x 10 <sup>9</sup> Ohms, 7 Days, un-cleaned
BELLCORE SIR (pass > 10 <sup>11</sup> )	7.3 x 10 <sup>11</sup> Ohms, 1 Day, un-cleaned
BELLCORE SIR (pass > 10 <sup>11</sup> )	3.5 x 10 <sup>11</sup> Ohms, 4 days, un-cleaned
Electromigration (500 hours) (BELLCORE)	1.6 x 10 <sup>11</sup> Ohms, 96 hours 4.0 x 10 <sup>11</sup> Ohms, 500 hours (pass: final > init /10)

**PROCESSING GUIDELINES**
**Reflow**

Reflow can be accomplished in dry air or nitrogen controlled atmosphere. The initial ramp rate should be 1 to 2 °C per second. If necessary, a dwell of 1 to 2 minutes at 130 to 160 °C is acceptable. Following this equilibrating period is a ramp of 60 to 120°C to a peak temperature of 235 to 260 °C depending upon alloy. The time above alloy liquidus (TAL) should be 45 to 90 seconds. Cooling rate should be 3 to 7 °C per second to room temperature.

**RECYCLING SERVICES**

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



**SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at [MacdermidAlpha.com/assembly-solutions/knowledge-base](http://MacdermidAlpha.com/assembly-solutions/knowledge-base).**

**STORAGE**

The flux should be stored in sealed containers and can be stored at room temperature up to 25 °C (77 °F) for up to 12 months. If the material has been refrigerated (stored @ 0 to 10 °C or 32 to 50 °F) then the container should be allowed to reach room temperature before opening in order to prevent moisture condensation from ambient air on the flux.

**CONTACT INFORMATION**

**To confirm this document is the most recent version, please contact [Assembly@MacDermidAlpha.com](mailto:Assembly@MacDermidAlpha.com)**

[www.macdermidalpha.com](http://www.macdermidalpha.com)

<p><b>North America</b> 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p><b>Europe</b> Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p><b>Asia</b> 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.